

LL-20075 AA				
Parameter	Unit	Specification	Result	Test method
MFI(190°C/2.16kg)	g/10min	0.65–0.86	0.71	ASTM D 1238
Density	g/cm ³	0.919–0.921	0.9206	HOECHST METHOD
Tensile Strength @ Yield (MD)	MPa	8	12	ASTM D 882
Tensile Strength @ Yield (TD)	MPa	8	11	ASTM D 882
Tensile Strength @ Break (MD)	MPa	11	21.6	ASTM D 882
Tensile Strength @ Break (TD)	MPa	11	20.2	ASTM D 882
Elongation @ Break (MD)	%	600	815	ASTM D 882
Elongation @ Break (TD)	%	600	932	ASTM D 882
Tear Strength (MD)	g/25micron	142.9	142.9	BP METHOD
Tear Strength (TD)	g/25micron	314.2	334.2	BP METHOD
Impact Strength (Dart)	g	81.5	81.5	ASTM D 1709

فیلم های صنعتی، بسته بندی، پالت استرچ، کشاورزی، ژئوممبران، کیسه مقاوم