

Product Data and Technical Information

POLYMER TYPE: POLYPROPYLENE HOMOPOLYMER

GRADE NAME : RG 1102 G

PACKING : PP bags of 25 kgs, 50 bags on a pallet shrinked by PE

APPLICATION : Thermoformed parts (high thickness or big size), tape, yarns, monofilaments, strapping, sheets

PRODUCT FEATURES : Homopolymer for extrusion and thermoforming applications with high melt stability

PROCESSING METHOD : Extrusion

Property	Test Method	Unit	Value
MFR (.230° C / 2.16 Kg)	ASTM D1238/L	gr/10min	1
Tensile Modulus of Elasticity (1mm/min)	ASTM D638	MPa	1400
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	34
Elongation at Yield(50 mm/min)	ASTM D638	%	10
Notched Charpy Impact at 23°	ISO 179/ 1eA	KJ/m2	6
Notched Charpy Impact at -30°	ISO 179/ 1eA	KJ/m2	2
Vicat Softening Point, 10N	ASTM D1525	°C	155
Ball indentation hardness	ISO 2039-1	MPa	70
HDT (0.46 N/mm2)	ASTM D648	°C	90
Melting Point , DSC	ASTM D3417	°C	163
Density	ASTM D792	gr/cm3	0.91

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests.