

Evonik Corporation Plexiglas® 8H PMMA Molding Compound

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

Description: PLEXIGLAS® 7H and PLEXIGLAS® 8H are molding compounds based on polymethyl methacrylate (PMMA). The special properties of these standard PLEXIGLAS® molding compounds are: high melt strength, high mechanical strength, surface hardness and abrasion resistance, high light transmission, excellent weather resistance, free colorability due to crystal clarity. The special properties of PLEXIGLAS® 8H compound are: optimum mechanical properties, increased heat deflection temperature, high melt strength, AMECA listing. Application: Used for extruding optical and technical profiles and sheets. Information provided by degussa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Plexiglas-8H-PMMA-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in³	ISO 1183
Melt Flow	0.952 g/10 min @Load 3.80 kg, Temperature 230 °C	0.952 g/10 min @Load 8.38 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	78.0 MPa	11300 psi	5 mm/min; ISO 527
Elongation at Break	6.5 %	6.5 %	5 mm/min; ISO 527
Tensile Modulus	3.30 GPa	479 ksi	1 mm/min; ISO 527
Charpy Impact Unnotched	2.00 J/cm² @Temperature 23.0 °C	9.52 ft-lb/in² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	80.0 µm/m-°C @Temperature 0.000 - 50.0 °C	44.4 µin/in-°F @Temperature 32.0 - 122 °F	ASTM E831
Vicat Softening Point	108 °C	226 °F	B50; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 707

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ISO 489
Transmission, Visible	92 %	92 %	Transmission Factor; DIN 5036

Optical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	220 - 260 °C	428 - 500 °F	Barrel Temperature
Die Temperature	220 - 260 °C	428 - 500 °F	
Melt Temperature	220 - 260 °C	428 - 500 °F	
Drying Temperature	<= 98.0 °C	<= 208 °F	Predrying
Dry Time	2 - 3 hour	2 - 3 hour	Desiccant-type drier

Descriptive Properties	Value	Comments
Fire Rating	B2	DIN 4102

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China