



Chloroprene rubber (CR) selection guide

The chloroprene rubber (CR) used in adhesives

Sundow SN	Modifier	Crystallization	Brook field viscosity, mPa s (25°C, toluene solution)		Dupont,SDK Neoprene	Lanxess Baypren	Denka	Tosoh Skyprene	Main application
			5%solid content	10% solid content					
SNR240T	Mercaptan	Fast	15-23		AD5	310	A-30	G42	Adhesive
SNR241	Mercaptan	Fast	25-35		AD10	310/320	A-70	G40S	
SNR242A	Mercaptan	Fast	34-40		AD20	320	A-90 A-91	G40S-1	
SNR242B	Mercaptan	Fast	41-53		AD20	320	A-90 A-91	G55 G40S-1	
SNR243	Mercaptan	Fast	54-75		AD30	330/340	A-100	G40T	Adhesive with higher tack.
SNR244	Mercaptan	Fast	76-115		AD40	340/350	A-120	G70	
SNR245T	Mercaptan + thiuram	Fast	31-45		AC	321	TA-85	G41H	Adhesive
SNR236T	Mercaptan	Medium		1000-1500	---	233 243	M-130L	Y30	Goods with highly loading, adhesive, conveyor belts, hoses, rubber seals, some hard goods.
SNR237T	Mercaptan	Medium		1800-3600	----	233 243	M-130H	Y30H	