

TYPICAL DATA SHEET*	ISSUE DATE	OCT 2024
HIGH IMPACT POLYSTYRENE(HIPS)	www.tpco.ir	
HIPS7240WB	IRAN/TABRIZ/TABRIZPETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

HIPS7240WB is very high impact polystyrene for the extrusion industry. This grade has been designed to dilute with crystal polystyrene. **Features:** The good melt strength of this grade makes it particularly suited for deep-draw thermoforming.HIPS7240WB is available in white blue color. This grade has food contact approval.

Processing Method: extrusion

Application: dirty sheet, cups, trays, egg boxes, general packaging, co extrusion with GPPS at industrial sheets.

Description

UNIT	TEST METHOD	TYPICAL VALUE
gr/10min	ASTM D-1238	4.5
ppm	CLG LABPSG004 (ATOFINA TEST METHOD)	<500
°C	ASTM D-1525	97
°c	ASTM D-648	81
-	ASTM D785	92 R SCALE
MPa	ASTM D638	23
MPa	ASTM D638	21
%	ASTM D638	60
MPa	ASTM D638	1950
KJ/m ²	ISO180/1A	11
gr/cm ³	ASTM D-792	1.04
%	ASTM D-955	0.55
-	ASTM E-313	-3
-	ASTM E-313	80
	gr/10min ppm °c °c - MPa MPa MPa MPa KJ/m² gr/cm³	gr/10min ASTM D-1238 ppm CLG LABPSG004 (ATOFINA TEST METHOD) °c ASTM D-1525 °c ASTM D-648 - ASTM D785 MPa ASTM D638 MPa ASTM D638 MPa ASTM D638 MPa ASTM D638 KJ/m² ISO180/1A gr/cm³ ASTM D-792 % ASTM D-955 - ASTM E-313

^{*} All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (Standard Sales Specifications. All tests are carried out at 23°C, unless otherwise stated.