

■ SN12系列

- 具有良好的加工特性。
- 易于塑炼、混炼，炼胶后胶片平整光滑，收缩小。
- 焦烧时间长，加工安全性高
- 广泛应用于制造动力传动带、输送带、防尘罩等汽车橡胶配件、CR泡棉等。



- Outstanding processing characteristics.
- Easy for plastication and milling. The slices after plastication or milling are smooth and of little shrinkage.
- Long scorching time, high processing safety.
- Widely used in the manufacture of rubber products with power transmission belt, conveyor belt, dust cover and other automotive rubber parts, CR foam and so on.

■ SN322X系列

- 与钢丝等金属粘着力强
- 加工安全性高，焦烧时间长
- 优良的加工性能
- 广泛应用于制造输送带、农机带、减震制品、胶管、阻尼块等橡胶制品。
- Strong adhesion to metal, such as steel wire.
- High processing safety and long scorching time
- Excellent processability
- Widely used in manufacturing conveyor belts, agricultural machinery belts, shock absorbing products, rubber hoses, damping blocks and other rubber products.

型号	门尼粘度ML ML ^{100℃ 1+4}	门尼焦烧 Min≥	500%定伸 MPa	拉伸强度 MPa≥	伸长率 % ≥	挥发分 ≤
SN121	30-50	25	2-5	23	850	0.8
SN122	51-65	25	2-5	23	850	0.8
SN322X-1	25-40	25	2-5	22	800	1.3
SN322X-2	41-60	25	2-5	22	800	1.3
SN322X-3	61-80	25	2-5	22	800	1.3