

■ 储存

- 自生产日期起, 20℃以下, 保质期为1年, 20℃-30℃, 保质期为半年。
- 贮存过程中, 应保持通风干燥, 避光防晒, 勿近热源, 防止受潮。

■ Storage

- From the date of production, below 20℃, the shelf life is 1 year; between 20℃-30℃, the shelf life is half a year.
- Keep under cover in a cool and well-ventilated place, avoiding direct sunlight or heating.



■ SN23系列

- 优异的挤出性能以及耐老化性能
- 良好的储存稳定性
- 加工安全性高, 焦烧时间长
- 可以做浅色橡胶制品
- 广泛应用于制造输送带、胶管胶辊、橡胶密封件、挤压型条、胶囊、空气弹簧、特种电缆护套, 也可以应用于胶黏剂领域调整开放时间。



- Excellent extrusion properties and aging resistance
- Good storage stability
- High processing safety and long scorching time
- Can be used to make rubber products of light color
- Widely used in manufacturing conveyor belts, rubber hose, rubber roll, rubber seals, extruded strips, capsules, air springs, and special cable sheath, also for adjusting the open time of adhesive.



型号	门尼粘度ML ML ^{100℃ 1+4}	门尼焦烧 Min ≥	500%定伸 MPa	拉伸强度 MPa ≥	伸长率 % ≥	挥发分 ≤
SN231	34-41	12	2-5	13	700	0.8
SN232	42-54	12	2-5	13	700	0.8
SN238	90-110	12	2-5	13	700	0.8
SN239	110-130	12	2-5	13	700	0.8