

GRADE	Mooney Viscosity (ML1+4 at 100°C)	Crystallization Rate	Main Applications
B-5	45~53	Very slow	-Wire and cable jackets -Automotive parts -General industrial parts
B-10	47~55		
B-30	45~53	Medium	-Sponge -Construction materials for buildings and public works
B-31	36~44		
E-20	45~53	Very slow	-Extruded products (various hoses, window frames, etc.) -Calendered products
E-33	45~53	Medium	
Y-20E	45~53		
Y-30*	111~35		
Y-31	90~110		
Y-30H*	1,460~2,500cps***		-Adhesives for high viscosity
R-10	40~60 (at the time of production)	Very slow	-Belts -Rolls -Wet suits -Thread rubber -Linings
R-22	35~55 (at the time of production)	Medium	
G-40S*	81~95**	Rapid	-MMA graft application -various Adhesives for Construction, automobiles, shoe-making, carpentry, tiles, etc.
G-40S-1*	81~95**		
G-40T*	96~113**		
G-41H*			