

Application

Oily paint

典型数据	Property	Company	SR-236
Tio2 质量分数	Tio2 content	%≥	93.0
金红石含量	Rutile content	%≥	97.0
无机包膜	Inorganic coating		硅、铝Si . Al
有机包膜	Organic treatment		Yes
105℃挥发物	Loss at 105℃	%≤	0.50
水溶物	Solution in water	%≤	0.5
筛余物	Residue	%≤	0.01
干粉白度 (WH)	Whiteness	%≥	96.5
L值	L Value	≥	98.0
消色力 (比标准样)	Tint reducing power	%≥	175
吸油量	Oil absorption , g/100g	≤	18-22
水悬浮液PH值	PH		6.5-8.5
电阻率	Specific resistance	Ωcm ≥	8500